

VEBE FLOORCOVERINGS B.V.

De heer Erik de Roode
Inslag 12
NL- 8281 JV
Genemuiden
Nederland

contact

Didier Van Daele

e-mail

didier.vandaele@UGent.be

Date

18/06/14

TEST REPORT 14-456A

Samples received :

Metal VL
Lab order 14.2073
Received on 22/05/2014

Aim of the test :

Fire behaviour

Test conditions :

Fire Behaviour

Standard:

EN ISO 9239-1 (2010)*

Method:

Before the test the samples are **not cleaned** with a spray-extraction machine. A floorcovering is put into an aluminum frame 719547(Emco). During the test, the specimen is irradiated by a gas radiator at an angle of 30°. A small flame is used to ignite the specimen. The specimen is ignited during 10 minutes. In case of inflammable specimens, the test lasts until the flame is extinguished, but 30 minutes at the most. The criterion is the burned length, from which the critical radiant flux is deduced using a calibration curve.

The test EN 11925-2 has not been performed because the floorcovering fulfills the requirements of EN 14041 section 4.1.4 table 2. The floorcovering has a total mass of 1720 g/m² and a pile thickness of 4.0 mm as declared by the customer.

Number of tests:

4

Measurement
uncertainty:

The relative reproducibility for 3 repetitions is 15.6% for the flux, 84.5% for the smoke development.

Conditioning samples: 23 ± 2 °C and 50 ± 5 % R.H.

The tests were performed in week 23/2014

OBTAINED RESULTS

Specimen number	1 Length	2 Width	3 Length	4 Length	Average Specimens 1,3,4
Flame spread after 10 min (mm)	110	60	90	130	
Flame spread after 20 min (mm)	110	60	90	130	
Flame spread after 30 min (mm)	110	60	90	130	
Flame spread at extinction (mm)	110	60	90	130	
Flame time	12min 0s	12min 0s	12min 0s	12min 0s	
Critical heat flux CHF at extinction (kW/m ²)	10.6	11.1	10.9	10.4	≥11
Total smoke production at end of test (%.min)	29	45	31	52	37

Didier Van Daele
Head of floorcovering/fire tests

Prof. Dr. Paul KIEKENS, dr. h. c.
Head of Department

ENCLOSURE TO REPORT 14-456A

*Classification according to EN 13501 –1 (2007 + A1: 2009)**

Classification	EN ISO 11925-2 (ignition time = 15 s)	EN ISO 9239-1 (test period = 30 min)	CLASS
B _{fi}	F _s ≤ 150 mm in 20 s	Critical flux ≥ 8.0 kW/m ²	X
C _{fi}	F _s ≤ 150 mm in 20 s	Critical flux ≥ 4.5 kW/m ²	
D _{fi}	F _s ≤ 150 mm in 20 s	Critical flux ≥ 3.0 kW/m ²	
E _{fi}	F _s ≤ 150 mm in 20 s	No demand	
F _{fi}	No demand	No demand	

*Additional classification smoke development according to EN 13501-1 (2007 + A1:2009)**

		CLASS
Smoke development ≤ 750%.min	s1	X
Smoke development > 750%.min	s2	